

PROfila

ProFila Filament Datasheet Material: PETG X

PREMIUM FILAMENT

Suggested printing specs.	Value	Unit	Standard
Extruder Temperature	230-250	°C	Internal
Bed Temperature	90-105	°C	Internal
Print speed	50-70	mm/s	Internal
Fan	0-20	%	Internal
Minimum Nozzle Diameter	0,3	mm	Internal

Material Properties	Value	Unit	Standard
Density	1.27	g/cm ³	ISO 1183
Water Absorption	0.13	%	ISO 62
Tensile Strength at Break	26	MPa	ISO 527
Charpy Impact at 23°C	7.9	kJ/m ²	ISO 180
Hardness	105	sh/R	ASTM D785
Melting point	240	°C	ISO 11357
Heat distortion temperature	70	°C	ISO 75
Vicat Softening Temperature	78	°C	ISO 306

DISCLAIMER

The Information presented herein has been compiled from sources considered to be dependable and is accurate to the best of our knowledge. However, since data, safety standards, and government regulations are subject to change and the conditions of handling and use, or misuse, are beyond our control, ProFila Filaments makes no warranty expressed or implied, with respect to completeness or continuing accuracy of the information contained herein and disclaims all liability for reliance thereon.

User should satisfy himself that he has all current data relevant to his particular use.